

ALPHA[®] 615 SERIES Super RMA Flux

DESCRIPTION

ALPHA 615 flux meets MIL-F-14256 requirements for flux type RMA, making it suitable for all Military work requiring conformance to DOD-STD-2000. **ALPHA 615** also meets the IPC-J-004 standard for type ROL0, the lowest flux residue corrosivity category and the highest surface insulation resistance rating.

The standard solids content for 615 is 37%. Where use of a lower solids flux is appropriate, such as when wave soldering surface mount boards, 615-25 (25% solids) and 615-15 (15% solids) are available.

FEATURES & BENEFITS

- Maximum achievable RMA activity. Very fast wetting flux.
- Very cleanable, even with high preheat. No white residue.
- Excellent foaming properties. Uniform, consistent flux coverage.

ACTIVITY

ALPHA 615 is the most effective soldering flux yet developed for achieving excellent soldering yields with complex Military assemblies, while clearly passing all requirements for an RMA, non-conductive, non-corrosive flux.

Wetting balance and solder spread tests are widely used quantitative measures for comparing flux activity. The faster the speed of solder wetting, as measured by the wetting balance, and the greater the area of solder spread, i.e. spread factor percent, the more efficient the flux is for promoting solder wetting. The superior activity of 615 can be seen from the following test data:

	Alpha 615	Kester 185	Almit RF35M
Spread Factor ¹	91.7%	90.2%	86.8%
Wetting Speed ²	0.41 seconds	0.47 seconds	0.64 seconds

¹ Test conducted using oxidized copper and 60Sn/40Pb flowed at 500°F for 15 seconds.

² Test conducted using oxidized copper, 60Sn/40Pb at 500°F, 5 mm immersion depth and 10 second cycle time. Wetting speed measured as time for wetting to reach equilibrium.

ALPHA 615 has also demonstrated the ability to prevent solder icicle formation, when tested according to the method developed by Philips-Eindhoven, Netherlands, "Determination of the Flux Efficiency to Prevent Formation of Icicles (and Bridges)."

SAFETY

ALPHA 615 is flammable. Keep away from heat, sparks and open flames. Observe standard precautions for handling and use, such as in well-ventilated areas and avoidance of prolonged or repeated contact with skin.

PACKAGING

ALPHA 615 series fluxes are available in 1, 5 and 55 gallon containers.

SM325-6 2014-09-26

an Alent plc Company

ALPHA Global Headquarters
300 Atrium Drive, Somerset, NJ 08873 USA • 1-800-367-5460 • www.alpha.alent.com

The information contained herein is based on data considered accurate and is offered at no charge. No warranty is expressed or implied regarding the accuracy of this data. Liability is expressly disclaimed for any loss or injury arising out of the use of this information or the use of any materials designated.

ALPHA is a registered trademark of Alpha Metals, Inc.

© 2014 ALPHA

ALPHA[®] 615 SERIES Super RMA Flux

USE

ALPHA 615 is designed for wave soldering printed circuit assemblies that must use an RMA flux meeting military specifications. While formulated to have excellent foaming properties, wave and spray fluxing can also be used.

All three solids levels of 615 flux should be maintained by periodic measurement of flux specific gravity (corrected to 77°F) and kept to within +0.015 and -0.005 of the nominal values.

While topside preheat temperatures of 180-200°F are sufficient for 615 flux activation, higher preheat conditions may be required for assemblies that have significant heat sinking characteristics, or when attempting to minimize the temperature gradient that ceramic chip components see between preheat and the solder wave.

Under conditions of extreme preheat, most RMA fluxes become extremely difficult to clean after soldering, especially with mild fluorocarbon-blend solvents. ALPHA 615 flux residues clean very well with either mild fluorocarbon-blend solvents or aqueous saponifier (Alpha 2110).

TECHNICAL SPECIFICATIONS

Physical Properties	Typical Values		
	615	615-25	615-15
Appearance		Clear, amber liquid	
Specific Gravity @ 77°F ± .005	0.878	0.845	0.818
Solids Content, % wt/wt	37	25	15
Water Extract Resistivity, ohm-cm, per MIL-F-14256, typical	170,000	190,000	225,000
Chlorides and Bromides, per MIL-F-14256 (Silver Chromate Paper)	Pass	Pass	Pass
Copper Mirror, per MIL-F-14256	Pass	Pass	Pass
Copper Corrosion, IPC-J-STD-004	No Corrosion	No Corrosion	No Corrosion
Surface Insulation Resistance:			
35°C/90% RH, comb-down, uncleaned, per Bellcore GR-78, CORE Issue 1		> 1.0 x 10 ¹¹ ohms	
85°C/85% RH, comb-down, uncleaned, per IPC-SF-818, Class 3		>1.0 x 10 ⁹ ohms	
Flash Point (T.C.C.)		53°F	
Recommended Alpha Thinner		438	